



Fiberglass Coatings Inc.

WWW.FGCI.COM 800-272-7890

St. Petersburg 4301 a 34th St. North
Ft. Lauderdale 5553 Anglers Ave. Ste. 105

CATALYST CONCENTRATION CHART

M.E.K.P. Peroxide Percent By Weight, Measured In Drops, CC & Fluid Ounces

Volume	Polyester Resin		Vinyl Ester Resin	Gelcoat			
	1%	1-1/2%		1-1/4%	1-1/2%	1-3/4%	2%
1 oz	0.3 cc 9 drops	0.44 cc 13 drops	**	0.4 cc 12 drops	0.5 cc 15 drops	0.6 cc 17 drops	0.7 cc 20 drops
2 oz	0.6 cc 17 drops	0.9 cc 26 drops	**	0.8 cc 25 drops	1.0 cc 30 drops	1.2 cc 35 drops	1.3 cc 40 drops
4 oz	1.2 cc 35 drops	1.7 cc 52 drops	**	1.7 cc 50 drops	2.0 cc 60 drops	2.3 cc 69 drops	2.6 cc 79 drops
8 oz	2.3 cc 0.08 oz 70 drops	3.5 cc 0.12 oz 104 drops	4.6 cc .16 oz	3.3 cc 0.11 oz 100 drops	4.0 cc 0.13 oz 120 drops	4.6 cc 0.16 oz 138 drops	5.3 cc 0.18 oz 158 drops
1 Pint	4.6 cc 0.16 oz	7.0 cc 0.24 oz	9.3 cc .31 oz	6.6 cc 0.22 oz	7.9 cc 0.27 oz	9.8 cc 0.31 oz	10.6 cc 0.36 oz
1 Quart	9.3 cc 0.31 oz	13.0 cc 0.47 oz	18.5 cc .63 oz	13.2 cc 0.45 oz	15.9 cc 0.54 oz	18.5 cc 0.63 oz	21.2 cc 0.75 oz

One gallon of polyester resin weighs approximately 9.2 lbs. One gallon of gelcoat weighs approximately 10.5 lbs. The weight of MEKP 925 is 1.125 grams per cc. 30 drops is approximately equal to one cc.

cc = cubic centimeter. Oz = fluid ounce

Note: Using drops for catalyst measurement is only an estimate. In critical applications MEKP should be measured using cc's or fluid oz's which are volume measurements.

The percentages in the chart: 1% thru 2%, are percentages of resin or gelcoat by weight. The cc and oz values in the chart have been converted from weights of MEKP to volumes of MEKP.